

QUALITY IMPROVEMENT OF COATED PAPER

Patent number: JP8183145
Publication date: 1996-07-16
Inventor: DEIBITSUDO FUREDERITSUKU BEIRI; URURIKA EROFUSON; JIYON KUROODO HAZUBANDO
Applicant: ECC INT LTD
Classification:
 - international: **D21H19/44; D21H19/46; D21H19/82; D21H21/16; D21H19/00; D21H21/14; (IPC1-7): B32B29/00; B05D7/00**
 - european: **D21H19/44; D21H19/46; D21H19/82B; D21H21/16**
Application number: JP19950265892 19951013
Priority number(s): GB19940020777 19941014

Also published as:




EP0707112 (A1)
 GB2293991 (A)
 FI954803 (A)
 BR9504397 (A)

Report a data error here

Abstract of JP8183145

PROBLEM TO BE SOLVED: To coat a cellulose sheet base with two or more coatings capable of achieving a final surface of high quality having a final coating compsn. of a high solid concn. at a relatively high web speed in a coating machine.
SOLUTION: A method of more simplifying the coating a cellulose sheet material coated with at least one preparatory inorg. pigment-containing coating among final inorg. pigment-containing coatings is disclosed. The compounding of a sizing agent such as an alkyleketene dimer up to 2 wt.% to preparatory coatings or at least one of them based on the wt. of inorg. pigment is included. The compsn. used in this method is also disclosed.



Data supplied from the esp@cenet database - Worldwide

BEST AVAILABLE COPY



PATENT ABSTRACTS OF JAPAN

(11) Publication number: 08183145 A

(43) Date of publication of application: 16.07.1996

(51) Int. Cl. B32B 29/00
B05D 7/00

(21) Application number: 07265892
(22) Date of filing: 13.10.1995
(30) Priority: 14.10.1994 GB 94 9420777

(71) Applicant: ECC INTERNATL LTD
(72) Inventor: BAILEY DAVID FREDERICK
ELOFSSON ULRIKA
HUSBAND JOHN CLAUDE

(54) IMPROVEMENT OF QUANTITY OF COATED PAPER


(57) Abstract:

PROBLEM TO BE SOLVED: To coat a cellulose sheet base with two or more coatings capable of achieving a final surface of high quality having a final coating compsn. of a high solid concn. at a relatively high web speed in a coating machine.

SOLUTION: A method of more simplifying the coating a cellulose sheet material coated with at least one preparatory inorg. pigment-containing coating among final inorg. pigment-containing coatings is disclosed. The compounding of a sizing agent such as an alkyleketene dimer up to 2 wt.% to preparatory coat-

ings or at least one of them based on the wt. of inorg. pigment is included. The compsn. used in this method is also disclosed.

COPYRIGHT: (C)1996,JPO



BEST AVAILABLE COPY